





Technical Data Sheet
Creator WG
 Peel-off polyester coating

| DESCRIPTION | | | |
|--|---|--------------|----------------|
| <p>Creator WG (Weather Guard) is a two-component flexible polyester film-forming compound. . It is intended for masking surfaces of moulds or models for protection against damage and weather. The product is to be sprayed on smooth, non-absorbing substrates coated with a separating wax barrier. The film can be easily removed without leaving any residue. With its components mixed, the product has a viscosity at which it is ready to be applied.</p> | | | |
| COMPLEMENTARY PRODUCTS | | | |
| Cetox 200E | Hardener | | |
| SUBSTRATES | | | |
| Tooling pastes, gelcoats | Remove dust, next apply layer release agent | | |
| Creator Gloss | Remove dust, next apply layer release agent | | |
| <p>CAUTION: do not apply the product on rough or absorbing surfaces. Before covering the whole element, it is recommended to check the compatibility and effect of Creator WG on a smaller area.</p> | | | |
| MIXING RATIO | | | |
|  | Creator WG CETOX 20 OE | Weight ratio | Volume ratio |
| | | 100g 4-5g | 100ml 6-7ml |
| <p>CAUTION: Mix ingredients very thoroughly.</p> | | | |
| CONTENT OF VOLATILE ORGANIC COMPOUNDS (VOC) | | | |
| VOC II/B/c limit* | | 540 g/l | |
| Actual VOC content | | 300 g/l | |
| <p>* For ready to use mixture acc. to EU Directive 2004/42/CE</p> | | | |
| APPLICATION LIFE FROM MIXING WITH THE HARDENER | | | |
|  | 20 min at 21°C | | |
| DRYING TIME | | | |
|  | 3 hours at 21°C | | |

| | | | |
|---|------------------|---------------------|----------------------|
| COLOUR | | | |
| White | | | |
| APPLICATION CONDITIONS | | | |
| It is recommended to apply the primer at a temperature above 10°C and a humidity of no more than 80 %. | | | |
| APPLICATION | | | |
|  | Nozzle 2,5 mm | Pressure 2-3 bar | Distance 15-20 cm |
| YIELD | | | |
| Do not exceed 450 µm in a single layer. Use maximum 2 layers at 15-20 minutes intervals. Yield is from 500 to 800 g/m ² | | | |
| EQUIPMENT CLEANING | | | |
| THIN 880 spray filler thinner or NC solvent. | | | |
| STORAGE CONDITIONS | | | |
| Store in a cool dry room, away from sources of fire and heat. Avoid direct exposure to sunlight. | | | |
| SHELF LIFE | | | |
| Creator WG | 12 months/20°C | | |
| CETOX-200E | 18 months/20°C | | |
| SAFETY | | | |
| See Safety Data Sheet | | | |
| NOTES | | | |
| Intended for professional use only. | | | |
| OTHER INFORMATION | | | |
| Registration number: 000024104 | | | |
| The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control. | | | |