








**Technical data sheet**  
**PROFICYNK**  
 Putty for zinc and aluminium

<b>PROPERTIES</b>		
<p><b>PROFICYNK</b> putty – top quality filling putty. Excellent adhesion to various substrates (especially zinc coatings and aluminium). The product has high thermal resistance which allows it to keep adhesion to galvanised steel in high temperatures. It has excellent application parameters, short curing time, easy sandability and good mechanical properties.</p>		
<b>SUBSTRATES</b>		
polyester laminates	dry sand with P80-P120 and degrease again with the PLUS 780 silicone degreaser	
steel	degrease, dry sand with P80 – P120, degrease again	
galvanised steel	degrease, mat with an abrasive finishing pad and degrease again	
aluminium	degrease, mat with an abrasive finishing pad and degrease again	
two-component acrylic fillers	degrease, dry sand with P220 – P280, degrease again	
old paint coatings	degrease, dry sand with P220 – P280, degrease again	
<b>CAUTION</b>		
<p>Do not apply polyester putty directly on top wash primers or one-component acrylic and nitrocellulose products.</p>		
<b>MIXING RATIO</b>		
	PUTTY HARDENER	Weight ratio
		100g 2g
<b>APPLICATION LIFE FROM MIXING WITH THE HARDENER</b>		
4 to 6 min at 20°C.		

DRYING TIME					
20 to 30 min at 20°C. The time can be shortened by heating for 10 minutes at a maximum of 60°C.					
COATABILITY					
Finishing polyester putty, spray polyester filler, acrylic primers, epoxy primers					
APPLICATION CONDITIONS					
The minimum application temperature is +10°C					
APPLICATION					
	Clean and sand the surface				
	Degrease the surface with PLUS 780				
	Observe the required amount of hardener. Mix the components thoroughly until a uniform colour is obtained. Weight quantity of components: Add 100 g of PROFICYNK to 2 g of Hardener.  Binding time: 4 to 6 minutes at 20°C				
	Apply a layer of 5 mm max with a putty knife.				
	Wait for 20 to 30 minutes (at 20°C)				
	<table border="1" style="width: 100%; text-align: center;"> <tr> <td>rough</td> <td>finish</td> </tr> <tr> <td>P80 – P120</td> <td>P120 – P240</td> </tr> </table>	rough	finish	P80 – P120	P120 – P240
rough	finish				
P80 – P120	P120 – P240				
COLOUR					
Grey					

<b>CONTENT OF VOLATILE ORGANIC COMPOUNDS (VOC)</b>	
VOC II/B/b limit* = 250g/l	90 g/l
*For ready to use mixture.	
<b>EQUIPMENT CLEANING</b>	
THIN 850 acrylic thinner or NC solvent.	
<b>STORAGE CONDITIONS</b>	
Store in a cool dry room, away from sources of fire and heat. Avoid direct exposure to sunlight.	
<b>SHELF LIFE</b>	
PROFICYNK	24 months/20°C
Hardener	18 months/20°C
<b>SAFETY</b>	
See Safety Data Sheet.	
<b>NOTES</b>	
Intended for professional use only.	
<b>OTHER INFORMATION</b>	
Registration number: 000024104  The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.	